

COOKING POT HANDLE FRAGMENT V.008.2/2948.1. – LEADED BRONZE – ROMAN TIMES – SWITZERLAND

Artefact name Cooking pot handle fragment V.008.2/2948.1.

Authors Christian. Degriigny (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland) & Lucile. Ruynat (HE-Arc CR, None) & Valentin. Boissonnas (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland)

Url /artefacts/1113/

∨ The object



Fig. 1: Cooking pot handle before and after treatment, front (a and c) and back (b and d),

Credit HE-Arc CR, L.Ruynat.

∨ Description and visual observation

Description of the artefact	The object is the tip of a cooking pot handle representative of the Augustan age (100 AD), recognisable by the axial symmetry and the two orifices surrounded by prominent edging and flared shape. The upper part is composed of an openwork flower with three petals, comparable to the representation of the fleur-de-lis. A curved pattern frieze can be seen in the centre of the object. No decoration was found on the back. Before treatment, the object was covered with green corrosion products and organic remains, most of which were mineralised (Figs. 1a and b). Dimensions : L = 73 mm ; W = 48 ; T = 9 mm ; WT = 80.8 g.
Type of artefact	Household implement
Origin	Romans legionnaires' camp of Vindonissa (present-day town of Windisch), Aargau canton, CH., Windisch, Aargau, Switzerland
Recovering date	2008
Chronology category	Roman Times
chronology tpq	<input type="text" value="1"/> A.D. ▾
chronology taq	<input type="text" value="100"/> A.D. ▾
Chronology comment	1st century AD

Burial conditions / environment	Soil
Artefact location	Archaeological Service of the Aargau canton, Brugg, Aargau
Owner	Archaeological Service of the Aargau canton, Brugg, Aargau
Inv. number	V.008.2/2948.1. (Inv. Number at HE-Arc: 2001)
Recorded conservation data	2008: Probably a first sediment clearing by archaeologists during the excavation. 2016-17: Lucile Ruynat, mechanical removal of the corrosion products over the limitos with ultrasonic scalpel. Conservation of wooden remains at the top right of the front of the object. Protective layer (varnish) with acrylic resin Paraloid B72®.

Complementary information

The soil of Windisch is on the border between calcareous soil (Jura) and molasses-type (Swiss plateau). Calcareous soils tend to be alkaline whereas the molassic soil is generally more neutral. The Swiss climate is temperate, with the four marked seasons. It can have strong frosts in winter.

Study area(s)




Fig. 2: Cooking pot handle after treatment: front (left) and back (right). Location of sampling for SEM-EDS and Raman (red square 1), XRD analyses (red squares 1 and 2), as well as XRF analyses (blue points 3, 4, 5),


Credit HE-Arc CR, L.Ruynat.

Binocular observation and representation of the corrosion structure

The stratigraphy below gives an overview of the corrosion layers encountered on the object from visual macroscopic observation. The stratigraphy was created before treatment by observation under a binocular microscope and modified during the mechanical removal of corrosion products.

Fig. 3: Stratigraphic representation of the cooking pot handle fragment in cross-section based on macroscopic global observation and indication of Fig. 4,

Fig. 4



S1	Sediments with sand forming isolated and highly porous ochre-colored clusters
CP1	Scattered clusters of highly porous medium green corrosion product
CP2	Continuous layer of compact dark green corrosion product
SV1	Structural voids within CP2
POM1	Pseudomorphs of organic remains
POM2	Pseudomorphs of wood remains
CP3	Scattered clusters of highly porous light green corrosion product
CP4	Discontinuous layer of compact dark-red corrosion products
CP5	Discontinuous layer of compact red corrosion product
M1	Continuous and compact metal

Credit HE-Arc CR, L.Ruynat.

∨ MiCorr stratigraphy(ies) – Bi




Fig. 4: Stratigraphic representation of the corrosion structure of the cooking pot handle fragment observed macroscopically under binocular microscope using the MiCorr application (to be compared to Fig. 3). The stratum SV1 is integrated in CP2 while POM1 and POM2 are merged as POM1. The characteristics of the strata are only accessible by clicking on the drawing that redirects you to the search tool by stratigraphy representation, Credit HE-Arc CR, L.Ruynat.

∨ Sample(s)

Description of sample	No sample from the metal was possible. Only a few invasive samples were taken for analysis of corrosion products, as indicated on figure 2 (red squares 1 and 2).
Alloy	Leaded Bronze
Technology	As-cast
Lab number of sample	None
Sample location	None

Responsible institution Archaeological Service of the Aargau canton, Brugg, Aargau

Date and aim of sampling 2017, chemical analyses

Complementary information

None.

∨ Analyses and results

Analyses performed:

XRF with portable X-ray fluorescence spectrometer (NITON XL3t 950 Air GOLDD+ analyser, Thermo Fischer®). XRD of powder samples using Stoe Mark II-Imaging Plate Diffractometer System (Stoe & Cie, 2015) equipped with a graphite-monochromator. Mo-K α radiation ($\lambda = 0.71073\text{\AA}$, beam diameter 0.5 mm, exposure time: 10 min). SEM/EDS on the object. Raman on powder samples of corrosion products. SEM on sample of organic remains, as well as X-ray picture not presented in this report.

∨ Non invasive analysis

XRF analysis carried out after the cleaning process (Fig. 2, blue dot 3) showed that the metal is a leaded bronze (Table 1). Theoretically the metal is as-cast and should present a dendritic structure.

Elements mass %	Cu	Sn	Pb	Sb	Si	P	Ti	Fe
M1	61.1	21.1	14.2	0.9	0.9	0.4	0.2	0.1

Table

1: Chemical composition of the metal. Method of analysis: XRF, mode General metals, 60s (filters M20/Lo20/Li20). Located at point 3 Figure 2, UR-Arc CR.

XRF analyses of CP4 (Fig. 2, blue dot 5) and CP5 (Fig. 2, blue dot 4) are given in Table 2.

Elements mass %	Cu	Sn	Pb	Sb	As	Ag	Fe	P	Cl	S	BAL
Dark-red layer (CP4)	24.9	18.2	11.2	0.7	0.1	0.09	0.1	0.3	0.4	7.2	36.1
Red area layer (CP5)	33.5	14.5	16	0.5	0.8	0.1	0.05	1.3	0.6	1.5	30.5

Table 2: Chemical compositions of the dark-red and the red layers. Method of analysis: XRF, mode mining Cu/Zn, 180s (filters M30/Lo30/H60/Li60). BAL corresponds to the elements not analysed: O and C, UR-Arc CR.

✖ Metal

The mechanical removal of corrosion products stopped at the limitos, so the metal was not directly observed. Based on Table 1, it seems to be a leaded bronze.

Microstructure	Dendritic structure
First metal element	Cu
Other metal elements	Sn, Pb

Complementary information

None.

✖ Corrosion layers

Above the well-preserved metal core, CP4 is discontinuously interlocked in CP5. The XRD analysis done on a sample (Fig. 2, red square 2) of both corrosion products, shows that they are mainly constituted of cuprite (Cu_2O), (Fig. 5). The colour difference can be explained by a tin enrichment in the darker CP4, as measured by XRF (Table 2). The EDS analysis of the light green CP3 (red square 1 Fig. 2) layer did not reveal the presence of chlorides (Fig. 6). Complementary XRD analysis validated the absence of nantokite. Indeed the XRD and Raman indexing was not successful probably because the compound has a large amorphous part. The other layers were not analysed, we expect CP1 and CP2 to be malachite (copper carbonate hydroxyde) because of the green colour and absence of chlorides. Organic remains were mineralised and preserved by the corrosion process.




Fig.5: XRD spectrum of CP4 and CP5, Method of analysis: XRD, Center for X-ray Analytics, Empa,

Credit Empa, A.Neels.




Fig. 6: EDS spectrum representative of the light green corrosion product (CP3). Method of analysis: SEM-EDS, Lab of Electronic Microscopy and Microanalysis, IMA (Néode), HEI Arc,

Credit HEI, S.Ramseyer.

Corrosion form	Uniform
Corrosion type	Mostly type I with locally type II (Robbiola)

Complementary information

None.

✧ MiCorr stratigraphy(ies) – CS

✧ Synthesis of the binocular / cross-section examination of the corrosion structure

The schematic representation of corrosion layers of Fig.3 integrating additional information based on the analyses carried out is given in Fig. 7.




Fig. 7: Improved stratigraphic representation of the cooking pot handle fragment from visual observations and analyses,

S1: Sediments	Soil and sand
CP1: Outer light green corrosion clusters	Malachite?
CP2: Outer dark green corrosion layer	Malachite?
SV1	Structural voids within CP2
POM1: Pseudomorphs of organic remains	Stems, grass within CP2
POM2: Pseudomorphs of organic remains	Wood within CP2
CP3: Outer/inner isolated light green corrosion product	No Nantokite, No Malachite
CP4: Inner black-dark red corrosion layer	Main phase: Cuprite Tin enrichment
CP5: Inner red corrosion layer	Main phase: Cuprite
M1: Orange Metal	Bronze with high lead content, probably with dendrites (as-cast)

Credit HE-Arc CR, L.Ruynat.

✧ Conclusion

The object is a leaded bronze with a well-preserved metal core. Covering the metal are two strata (CP4 and CP5) composed of cuprite, the darker (CP4) appears enriched in tin. The superior interface of these layers represents the limitos. In areas the limitos, CP4 and CP5 have been replaced by a light green porous corrosion product (CP3). The following layers CP2 and CP1 are probably malachite.

The powdery green corrosion layer CP3 has frequently been observed on bronzes of Vindonissa where it can be located within cuprite or malachite layers. It is typically developed below the limitos and renders the latter extremely fragile. The nature of this corrosion product has not yet been determined. However, the absence of chlorine indicates that it is not a chlorinated corrosion product such as atacamite or paratacamite. The aggressive urban soil could be a reason for the transformation of these naturally grown and stable corrosion layers.

✧ References

References on object and sample

1. Käch, D. (2012) Jahresbericht 2011, Gesellschaft Pro Vindonissa, Brugg.
2. Käch, D. (2013) Jahresbericht 2012, Gesellschaft Pro Vindonissa, Brugg.
3. Holliger, C. (1984) "Bronzegefässe aus Vindonissa », In: Jahresbericht, Zürich, p.47-70.
4. Martin, M. (1994) Objets quotidiens de l'époque Romaine, Musée Romain d'Augst, Augst.

References on analytic methods and interpretation

5. Feugere, M. (1994) « La vaisselle gallo-romaine en bronze de Vertault (Côte-d'Or) », In : Revue Archéologique de l'Est et du Centre-Est, p.137-166. [Consulté le 22.03.2016] <https://halshs.archives-ouvertes.fr/halshs-00580295/document>
6. Montandon, B. (1997) Le travail du bronze à l'époque Gallo-Romaine, In Chronozones, n°3, p.2-11.
7. Picon, M. et al. (1996) « Recherches techniques sur des bronzes de Gaule romaine ». In: Gallia, tome 24, n°1, p. 189-215.
8. Robbiola, L. et al. (1998) «Morphology and mechanisms of formation of natural patinas on archaeological Cu-Sn alloys», In Corrosion Science, N°40, p. 2083-2111.
9. Robbiola, L. (1990) « Caractérisation de l'altération de bronzes archéologiques enfouis à partir d'un corpus d'objets de l'Age du bronze. Mécanismes de corrosion ». Thèse de Doctorat, Université Pierre et Marie Curie - Paris VI, Paris. In HAL archives ouvertes [En ligne]. HAL, 2010 [Consulté le 03.06.2017] <https://tel.archives-ouvertes.fr/tel-00495356/document>
10. Scott, D.A. (2002) Copper and bronze in Art, corrosion, colorants, conservation. Getty publications, Los Angeles.
11. Scott, D.A. (1987) « Metallography of Ancient Metallic Artifacts ». Institute of Archaeology, Summer Schools Press, London, pp. 3-17 and 128-132.
12. Selwyn, L. (2004) Métaux et corrosion, un manuel pour le professionnel de la conservation. ICC-CCI, Ottawa.