

COFFEE FILTER – AL ALLOY – MODERN TIMES – FRANCE

Artefact name Coffee filter

Authors Christian. Degriigny (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland)

Url /artefacts/369/

∨ The object



Fig. 1: Front and back sides of a coffee filter,

Credit HE-Arc CR, J.Schröter.

∨ Description and visual observation

Description of the artefact	Coffee filter with traces of use (deposits, deformation) and presence of local filiform corrosion (Fig. 1). Dimensions: ø.ext. = 10cm.
Type of artefact	Household implement
Origin	Château de Germolles, Mellecey, Bourgogne, France
Recovering date	Unknown
Chronology category	Modern Times
chronology tpq	<input type="text" value="1801"/> A.D. ∨
chronology taq	<input type="text" value="2000"/> A.D. ∨
Chronology comment	19th - 20th century
Burial conditions / environment	Outdoor atmosphere
Artefact location	Château de Germolles, Mellecey, Bourgogne
Owner	Château de Germolles, Mellecey, Bourgogne

Inv. number None
Recorded conservation data Not conserved

Complementary information


Nothing to report.

Study area(s)



Credit HE-Arc CR, J.Schröter.

Fig. 2: Detail of the front and back sides of the coffee filter showing the location of Fig. 3,



Credit HE-Arc CR, J.Schröter.

Fig. 3: Detail of the back side of the coffee filter showing the location of the sampling area,


Binocular observation and representation of the corrosion structure

Stratigraphic representation: none.

MiCorr stratigraphy(ies) – Bi

Sample(s)

Fig. 4: Micrograph of the cross-section showing the location of Figs. 6, 8 and 9, dark field,



Credit HE-Arc CR, J.Schröter.

Description of sample	Sample cut from the back side of the coffee filter (Fig. 3).
Alloy	Al Alloy
Technology	None
Lab number of sample	
Sample location	HE-Arc CR, Neuchâtel, Neuchâtel
Responsible institution	HE-Arc CR, Neuchâtel, Neuchâtel
Date and aim of sampling	2017, the EtICAL project (a study of corrosion forms of aluminium alloys)

Complementary information

A second sample was taken and gave similar results.

∨ Analyses and results


Analyses performed:
Metallography, SEM/EDS.

∨ Non invasive analysis

∨ Metal


The metal is a relatively pure aluminium alloy with numerous elongated inclusions (Fig. 6). From their chemical composition they can be interpreted as Al₃Fe intermetallic compounds (Fig. 7). Inter- and transgranular corrosion has

developed so extensively that some grains (not elongated) are outlined (Fig. 8).




Credit HEI Arc, S.Ramseyer.

Fig. 6: SEM image of the metal sample from Fig. 4 (detail), BSE-mode. We observe the presence of numerous elongated inclusions,



Credit HEI Arc, S.Ramseyer.

Fig. 7: EDS spectrum of the elongated inclusions of Fig. 6,



Credit HEI Arc, S.Ramseyer.

Fig. 8: SEM image of the metal sample from Fig. 4 (detail), BSE-mode. Extensive inter- and transgranular corrosion has developed within the metal,

Microstructure	None
First metal element	Al
Other metal elements	Fe


Complementary information

Nothing to report.


Corrosion layers

The average thickness of the corrosion layer (CP1) is about 50mm, but may be thinner or thicker depending on the area. Intergranular corrosion has developed locally to extend the whole thickness of the metal. Analysis by SEM-EDS

indicates that the metal is, as expected, covered by an Al and O-rich layer containing chlorides (red spots on Fig. 9) and surprisingly Na (Figs. 10 and 11). Chlorides do not seem to form active corrosion. A new examination carried out after 4 months (Fig. 12) shows new forms of alteration with a local enrichment of Na, C and O (Na₂CO₃?).




Credit HEI Arc, S.Ramseyer.



Credit HEI Arc, S.Ramseyer.


Fig. 9: SEM picture (detail of Fig. 4 with location of EDS analyses of Fig. 10), BSE-mode. From bottom to top left: the metal (M1) in light grey, the corroded metal (CM1) and CP1. The mapped area of Fig. 11 is marked by a rectangle,

Fig. 10: EDS spectrum of red spots in Fig. 9,



Credit HEI Arc, S.Ramseyer.

Fig. 12: SEM image, BSE-mode, and elemental chemical distribution of the selected area of Fig. 9 after 4 months. Method of examination: SEM-EDS, Lab of Electronic Microscopy and Microanalysis, IMA (Néode), HEI Arc,



Credit HEI Arc, S.Ramseyer.

Fig. 11: SEM image, BSE-mode, and elemental chemical distribution of the selected area of Fig. 9. Method of examination: SEM-EDS, Lab of Electronic Microscopy and Microanalysis, IMA (Néode), HEI Arc,

Corrosion form Multiform - intergranular

Corrosion type None

Complementary information

Nothing to report.

∨ MiCorr stratigraphy(ies) – CS




Fig. 5: Stratigraphic representation of the object in cross-section using the MiCorr application. This representation can be compared to Fig. 9, Credit HE-Arc CR, C.Degrigny.

∨ Synthesis of the binocular / cross-section examination of the corrosion structure

Corrected stratigraphic representation: none.

∨ Conclusion

This aluminium alloy has a composition similar to a primary aluminium with an Al content between 99 and 99.8 mass%. The main impurity is Fe forming intermetallic (Al₃Fe) inclusions. The metal was stamped and punctured. It is covered by a relatively thick corrosion layer (probably aluminium oxide) due to filiform corrosion. Extensive intergranular corrosion has developed locally within the metal. Chlorides have been identified but the progress of the corrosion might be due to Na, C and O-rich compounds (Na₂CO₃?).

∨ References

References object

1. Degrigny, C. (2018) Etude, identification des objets en aluminium patrimonioniaux et classification de leurs forms de corrosion - projet EtICAL, rapport interne HE-Arc CR.

References sample

2. Degrigny, C. (2018) Etude, identification des objets en aluminium patrimonioniaux et classification de leurs forms de corrosion - projet EtICAL, rapport interne HE-Arc CR.

