

OVAL BRACELET WITH SURFACE DECORATIONS OF LINES AND INDENTATIONS MAH ANC. 2662 – LEADED BRONZE – LATE BRONZE AGE – SWITZERLAND

Artefact name	Oval bracelet with surface decorations of lines and indentations MAH anc. 2662
Authors	Marianne. Senn (EMPA, Dübendorf, Zurich, Switzerland) & Christian. Degrieny (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland)
Url	/artefacts/380/

≡ The object



Credit HE-Arc CR.

Fig. 1: Leaded bronze bracelet (after Paszthory 1985, Tafel 82),

≡ Description and visual observation


Description of the artefact	Bracelet with a dense, black lake patina (Fig. 1). The bracelet corresponds to the type of bracelet decorated on the outside with alternate of dashes and meanders (Paszthory 1985, 164). Two samples were taken from this object – only one is presented here (Fig. 2). Dimensions: Ø = around 6.1cm; WT = 98g.
Type of artefact	Jewellery
Origin	Les Eaux-Vives, Genève, Geneva, Switzerland
Recovering date	None
Chronology category	Late Bronze Age
chronology tpq	<input type="text" value="1000"/> B.C. ▼
chronology taq	<input type="text" value="----"/> ▼
Chronology comment	Hallstatt B2/3 (1000BC _ not defined)
Burial conditions / environment	Lake

Artefact location	Musées d'art et d'histoire, Genève, Geneva
Owner	Musées d'art et d'histoire, Genève, Geneva
Inv. number	MAH anc. 2662
Recorded conservation data	Not conserved

Complementary information

Nothing to report.

Study area(s)



Credit HE-Arc CR.


Fig. 2: Location of sampling area,

Binocular observation and representation of the corrosion structure

Stratigraphic representation: none.

MiCorr stratigraphy(ies) – Bi

Sample(s)



Credit HE-Arc CR.

Fig. 3: Micrograph of the cross-section showing the location of Figs. 5 to 8,

Description of sample	The sample is a section from one end of the bracelet (Fig. 2). Its dimensions are: L = 1.3mm and W = 0.3mm. The corrosion layer is relatively thick (Fig. 3).
Alloy	Leaded Bronze
Technology	As-cast
Lab number of sample	MAH 77-110-1a
Sample location	Musées d'art et d'histoire, Genève, Geneva
Responsible institution	Musées d'art et d'histoire, Genève, Geneva
Date and aim of sampling	1977, study of black and iron rich surface deposit on the object

Complementary information

Nothing to report.

Analyses and results

Analyses performed:
Metallography (etched with ferric chloride reagent), Vickers hardness testing, ICP-OES, SEM/EDS.

Non invasive analysis

Metal


The remaining metal is a leaded bronze (Table 1) with low porosity, light and dark-grey inclusions (Fig. 5). In bright field the unetched alpha-delta eutectoid appears light-blue (Fig. 5). Etching reveals the dendritic structure of an as-cast metal (Fig. 6) with an average hardness of HV1 100. The inclusions appear as dark-grey (Pb-rich) and light-grey (copper sulphide) (Fig. 6 and Table 2) while the alpha-delta eutectoid is white (Fig. 6). The pink alpha phase is cored.

Elements	Cu	Sn	Pb	Sb	As	Ni	Ag	Ni	Zn	Fe	Co	Bi
mass%	87.62	6.98	4.36	0.42	0.23	0.18	0.13	0.18	0.04	0.03	0.02	0.02

Table 1: Chemical composition of the metal. Method of analysis: ICP-OES, Laboratory of Analytical Chemistry, Empa.


Elements	S	Cu	Pb	Total
Light-grey inclusion	21	82	<	103
Dark-grey inclusion	<	2	92	94

Table 2: Chemical composition (mass %) of the inclusions on Fig. 5. Method of analysis: SEM/EDS, Laboratory of Analytical Chemistry, Empa.



Credit HE-Arc CR.

Fig. 5: Micrograph of the metal sample from Fig. 3 (detail), unetched, bright field. The metal is in pink, the Pb-rich inclusions in light-grey, the copper sulphide inclusions in dark-grey and the alpha-delta eutectoid in light-blue,



Credit HE-Arc CR.

Fig. 6: Micrograph similar to Fig. 5, etched, bright field. The dendritic structure of the leaded bronze is revealed with the alpha-delta eutectoid in white and the alpha phase in pink. The colour difference of the alpha phase is due to coring,

Microstructure	Dendritic structure with pores and inclusions
First metal element	Cu
Other metal elements	Sn, Pb


Nothing to report.

Corrosion layers

The corrosion crust has an average thickness of 80µm. It is composed of two layers (Fig. 7). The inner layer (CP2), which appears grey in bright field (Fig. 5), retains a Sn-rich dendritic ghost structure (Table 3 and Fig. 8). In polarized light, this layer is a mixture of reddish and yellow-brown corrosion products with some green areas (Fig. 7). The reddish parts have a composition similar to cuprite/Cu₂O (Table 3). The adjacent dense, cracked layer, which appears dark-grey in bright field (CP1), is mainly composed of Fe₂O₃ and Sn with Sn₂O₃ and Fe-rich and Fe and O-rich zones contaminated with Si while being depleted of Cu (Fig. 8). In polarised light, it is dark, almost black with some red areas. In areas it contains Ag, Fe and Sn-rich inclusions with traces of Pb and Cu (Fig. 8 and Table 3).

Elements	O	Pb	Fe	Cu	Si	Sn	Ag	Total
CP1, light-grey in Fig. 8	40	5.7	8.1	21	3.5	<	<	106
CP1, dark-grey in Fig. 8	30	5.3	19	3.7	3.1	<	<	99
CP1, bright inclusion	4.5	9.8	45	2.4	<	28	28	98
CP2, dendritic ghost structure	39	5.5	17	32	3	<	<	109
CP2, reddish part	14	<	77	3	<	<	<	96

Table 3: Chemical composition (mass %) of the corrosion layers from Figs. 7 and 8. Method of analysis: SEM/EDS, Laboratory of Analytical Chemistry, Empa.



Credit HE-Arc CR.

Fig. 7: Micrograph similar to Fig. 5 and corresponding to the stratigraphy of Fig. 4, polarised light. From bottom left to top right: the metal in brown, the dendritic ghost structure in red, yellow-brown and green and the outer corrosion layer in black with some red areas. The thin white line is a crack,




Fig. 8: EDS elemental chemical distribution in an SEM image (detail of Fig. 5, reversed picture). Method of examination: SEM/EDS, Laboratory of Analytical Chemistry, Empa,

Corrosion form Uniform - selective

Corrosion type Type II (Robbiola)

Complementary information

Nothing to report.

✧ MiCorr stratigraphy(ies) – CS




Fig. 4: Stratigraphic representation of the object in cross-section using the MiCorr application. This representation can be compared to Fig. 7, Credit HE-Arc CR.

✧ Synthesis of the binocular / cross-section examination of the corrosion structure

Corrected stratigraphic representation: none.

✧ Conclusion

The surface of the cast leaded bronze has been replaced by a Sn-rich corrosion that retains a dendritic ghost structure. It is composed of a mixture of copper oxides (cuprite?) and a Sn-rich corrosion product (cassiterite?). The outer corrosion layer is composed of Fe-O and Sn-O-Fe areas depleted of Cu, but contaminated with Si. The enrichment in Fe seems to be the same as for the formation of patinas from lake contexts. However the outer corrosion layer was not formed in anaerobic conditions (Fig. 7). Since the original surface is absent (destroyed) we refer to type corrosion 2 after Robbiola et al. 1998.

✧ References

References on object and sample

1. Boll, P. (1991) Empa-Bericht n° 137'695/1991, not published.
2. Mottier, Y., Schweizer, F. (1977, 1991) Rapport du Laboratoire de recherche des musées d'art et d'histoire, not published.
3. Paszthory, K. (1985) Der bronzzeitliche Arm- und Beinschmuck in der Schweiz. Prähistorische Bronzefunde X-Bd. 3, München 1985, 164, Tafel 82.

References on analytic methods and interpretation

4. Mottier, Y., Schweizer, F. (1977, 1991) Rapport du Laboratoire de recherche des musées d'art et d'histoire, not published.
5. Robbiola, L., Blengino, J-M., Fiaud, C. (1998) Morphology and mechanisms of formation of natural patinas on archaeological Cu-Sn alloys, Corrosion Science, 40, 12, 2083-2111.