

AIRCRAFT REAR FASTENING PLATE VHS-497 - AL ALLOY - MODERN TIMES

Artefact name Aircraft rear fastening plate VHS-497

Authors Marianne. Senn (EMPA, Dübendorf, Zurich, Switzerland) & Christian. Degrigny (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland)

Url /artefacts/391/

▼ The object




Fig. 1: Photograph of the aeroplane showing the location of the fixation plate (red dot) (www.hepta.aero).

Credit HE-Arc CR.

▼ Description and visual observation

Description of the artefact Fixation plate for the wooden construction at the back of the aeroplane (Fig. 1).

Type of artefact Aeroplane part

Origin Dufaux IV aeroplane

Recovering date Biplane built by Henri and Armand Dufaux in 1909/10

Chronology category Modern Times

chronology tpp A.D. ▾

chronology taq A.D. ▾

Chronology comment 1909 _ 1910

Burial conditions / environment Outdoor to indoor atmosphere

Artefact location Swiss Museum of Transport, Luzern, Lucerne

Owner Swiss Museum of Transport, Luzern, Lucerne

Inv. number VHS-497

Recorded conservation data Not known

Complementary information

Nothing to report.

▼ Study area(s)




Fig. 2: Location of sampling area,

Credit HE-Arc CR.

▼ Binocular observation and representation of the corrosion structure

Stratigraphic representation: none.

▼ MiCorr stratigraphy(ies) – Bi

▼ Sample(s)




Fig. 3: Micrograph of the cross-section showing the location of Figs. 5 to 11,

Credit HE-Arc CR.

Description of sample

Sample cut from the corner of the fixation plate (Fig. 2). Dimensions: L = 4mm ; W = 1.2mm.

Alloy	Al Alloy
Technology	Hot rolled and annealed
Lab number of sample	DUF-12
Sample location	Empa (Marianne Senn)
Responsible institution	Swiss Museum of Transport, Luzern, Lucerne
Date and aim of sampling	September 2007, metallography and alloy composition

Complementary information

Nothing to report.

▼ Analyses and results

Analyses performed:

Metallography (nital etched), Vickers hardness testing, SEM/EDS.

▼ Non invasive analysis

▼ Metal

The metal is a relatively pure aluminium alloy with numerous inclusions (Table 1). From the chemical composition of the inclusions they can be interpreted as alpha-AlFeSi intermetallic compounds. In bright field we observe elongated inclusions indicating that the metal was rolled (Fig. 5). The alloy composition is similar to an unalloyed primary aluminium (Al content between 99 and 99.8 mass%). The O content reflects the immediate oxidation of the metal and is not part of the alloy. After etching the organisation of inclusions in rows is more easily seen (Fig. 6). The SEM image shows large grains formed after annealing (Fig. 7). The average hardness of the metal is HV1 40.

Elements	Al	Si	Fe	O	Total
Metal (average)	95	0.8	<	0.7	97
Inclusion (average)	60	8.6	31	1.5	100

Table 1: Chemical composition (mass %) of the metal and inclusions (from Fig. 5). Method of analysis: SEM/EDS, Laboratory of Analytical Chemistry, Empa.




Fig. 5: Micrograph of the metal sample from Fig. 3 (detail), unetched, bright field. The metal matrix is in white, the elongated inclusions in grey,

Credit HE-Arc CR.




Fig. 6: Micrograph of the metal sample from Fig. 3 (detail), etched, bright field. The metal matrix is in white, the elongated inclusions in dark-grey and black,

Credit HE-Arc CR.




Fig. 7: SEM image of the metal sample from Fig. 3 (detail), SE-mode, etched. We observe the presence of large grains and numerous elongated inclusions,

Credit HE-Arc CR.

Microstructure

Recrystallized structure with large grains

First metal element

Al

Other metal elements


Si

Complementary information

Nothing to report.


▼ Corrosion layers

The metal is covered by a very thin corrosion layer (CP1). In addition to this, locally thicker “corrosion products” or adherent material can be observed (D1, appearing as dark-grey area in Fig. 8). Under polarized light, they appear blue-brown (Fig. 9). Analysis by SEM-EDS indicates that the metal is, as expected, covered by a very thin Al and O-rich layer whereas the particles in the adherent material contain C, O, Si, Ca, Fe, Zn, S and even Ti (Figs. 10 and 11). The location of the adherent material and the presence of both Zn and Ti suggest that it is a residue of a paint coating.



Credit HE-Arc CR.

Fig. 8: Micrograph showing the metal - “corrosion products” interface from Fig. 3 (reversed picture, detail), unetched, bright field. We observe in white the metal matrix and dark-grey the adhering material,



Credit HE-Arc CR.

Fig. 9: Micrograph (same as Fig. 8) and corresponding to the stratigraphy of Fig. 4, unetched, polarised light. We observe in grey the metal matrix and blue-brown the adherent material,




Fig. 10: SEM image (same as Fig. 8, inverted picture, detail), BSE-mode, unetched,

Credit HE-Arc CR.




Fig. 11: Elemental chemical distribution of the selected area from Fig. 10. Method of examination: SEM/EDS, Laboratory of Analytical Chemistry, Empa,

Corrosion form	Passive
Corrosion type	None

Complementary information

Nothing to report.

▼ MiCorr stratigraphy(ies) – CS




Fig. 4: Stratigraphic representation of the object in cross-section using the MiCorr application. This representation can be compared to Fig. 9, Credit HE-Arc CR.

▼ Synthesis of the binocular / cross-section examination of the corrosion structure

Corrected stratigraphic representation: none.

▼ Conclusion

This aluminium alloy has a composition similar to a primary aluminium with an Al content between 99 and 99.8 mass%. The main impurities are Si and Fe. Because of their insolubility in the aluminium they form intermetallic (alpha-AlFeSi) inclusions. The metal was hot rolled and annealed. It is covered by a very thin corrosion layer (probably aluminium oxide) and in some areas adherent materials are present, most likely the remains of a Zn- and Ti-rich paint system mixed with environmental pollutants.

▼ References

References object

1. Rumo, L. (2008) Analyse et caractérisation des alliages constitutifs de l'avion Dufaux IV. Mémoire Filière conservation-restauration, Haute Ecole art appliqués, La Chaux-de-Fonds, 101-105.

References sample

2. Rumo, L. (2008) Analyse et caractérisation des alliages constitutifs de l'avion Dufaux IV. Mémoire Filière conservation-restauration, Haute école art appliqués, La Chaux-de-Fonds, 101-105.

References on analytic methods and interpretation