

SWORD M-SCH-B2735 – P-RICH IRON – IRON AGE – SWITZERLAND

Artefact name	Sword M-Sch-B2735
Authors	Marianne. Senn (Empa, Dübendorf, Zurich, Switzerland) & Christian. Degrigny (HE-Arc CR, Neuchâtel, Neuchâtel, Switzerland)
Url	/artefacts/967/

∨ The object



Fig. 1: Sword (after Senn Bischofberger 2005, 241),

Credit HE-Arc CR.

∨ Description and visual observation

Description of the artefact	Sword of the middle la Tène type, broken into two parts (Fig. 1). Under a hand lens the surface shows parallel grinding traces from mechanical cleaning.
Type of artefact	Weapon
Origin	Marin-Epagnier, La Tène, Saint-Blaise, Neuchâtel, Switzerland
Recovering date	Water finds, end 19th/beginning 20th cent. AD
Chronology category	Iron Age
chronology tpq	<input type="text" value="250"/> B.C. ∨
chronology taq	<input type="text" value="140"/> B.C. ∨
Chronology comment	La Tène C
Burial conditions / environment	Soil
Artefact location	Museum Schwab, Biel/Bienne, Bern
Owner	Museum Schwab, Biel/Bienne, Bern
Inv. number	M-Sch-B2735
Recorded conservation data	Conserved (not recorded, but mechanical cleaning visible)

Complementary information

None.

Study area(s)



Credit HE-Arc CR.


Fig. 2: Location of sampling area,

Binocular observation and representation of the corrosion structure

None.

MiCorr stratigraphy(ies) – Bi

Sample(s)



Credit HE-Arc CR.

Fig. 3: Micrograph of the cross-section of the sample taken from the sword showing the location of Figs. 4 to 9,

Description of sample

The sample includes half of the sword blade (Figs. 2 and 3). The corrosion layer is thin (Fig. 3).

Alloy

P-rich iron

Technology

Forged, annealed and cold worked

Lab number of sample

M-SCH-B2735

Sample location	HE-Arc CR, Neuchâtel, Neuchâtel
Responsible institution	Schweizerisches Landesmuseum, Zürich, Zurich
Date and aim of sampling	1969, metallography

Complementary information

None.

∨ Analyses and results

Analyses performed:

Metallography (nital etched), Vickers hardness testing, LA-ICP-MS, SEM/EDS.

∨ Non invasive analysis

None.

∨ Metal

The remaining metal is a P-rich (0.2 mass%) iron (Table 1) with long parallel slag inclusions (Fig. 4) concentrated on one side of the blade. The slag inclusions are composed of wüstite/FeO dendrites and fayalite/Fe₂SiO₄ in a glassy matrix (Fig. 5 and Table 2). Their chemical composition is typical for iron produced by the bloomery process (dominated by iron oxides and silica). It is difficult to identify the ore type from the slag composition. Interestingly in one case the slag composition is very specific (alumina and P-rich material). After etching, the metal shows a ferritic structure (Fig. 6). The grain size is variable (between ASTM grain sizes of 4 to 7) and some grains include Neumann bands (Fig. 7). A large crack has developed through the metal section (Figs. 3 and 6). The average hardness of the metal (HV1 185) is quite high for a wrought iron. The level of hardness and Neumann bands are typical for a P-rich iron. Neumann bands are said to develop by cold working and shock deformation. According to Swiss and McDonnell 2003 they form when little cold work is carried out. Distortion (grain deformation) after cold working starts to be apparent in iron after a reduction in thickness of between 30-40%. Since no grain deformation is visible, the present reduction is probably a little less than this range.


Elements	V	Cr	Mn	P	Co	Ni	Cu	As	Ag
Median mg/kg	<	5	10	2200	140	270	500	260	<
Detection limit mg/kg	1	4	1	50	1	1	1	2	0.1
RSD %	-	56	48	10	14	16	37	15	-

Table 1: Chemical composition of the metal. Method of analysis: LA-ICP-MS, Lab Analytical Chemistry, Empa (for details see Devos et al. 2000).

Structure	MgO	Al ₂ O ₃	SiO ₂	P ₂ O ₅	K ₂ O	CaO	TiO ₂	MnO	FeO	Total	SiO ₂ /Al ₂ O ₃
Wüstite in glass	0.7	2.1	15	2.7	<	0.6	<	<	87	109	7.2


Wüstite and fayalite in glass	<	4.8	24	0.7	1	1.4	<	<	70	103	5.0
Wüstite and fayalite in glass	0.6	2.7	23	1.8	<	0.8	<	<	69	98	8.4
Fayalite in glass	<	5.6	26	2.8	0.8	1.4	<	<	72	110	4.8
Fayalite phase	0.8	1.0	31	1.2	0.7	1.1	<	0.8	69	106	33
Fayalite in glass	<	8.8	24	3.2	1.0	1.4	0.6	<	66	106	2.8

Table 2: Chemical composition of the slag inclusions (mass%) at the tip (pearlite) and the body (ferrite) of the knife. Method of analysis: SEM/EDS, Laboratory of Analytical Chemistry, Empa.



Credit HE-Arc CR.

Fig. 4: Micrograph of the metal sample from Fig. 3 (detail, rotated by 225°), unetched, bright field. In white the metal containing elongated slag inclusions (in grey); in black porosity.



Credit HE-Arc CR.

Fig. 5: Micrograph of the metal sample from Fig. 3 (detail), unetched, bright field. Detail with slag inclusions showing a structure with wüstite dendrite (light-grey) and fayalite (dark-grey).




Fig. 6: Micrograph of the metal sample from Fig. 3 (reversed picture, rotated by 225°, detail), etched, bright field. Metal with a large pre-existing crack and ferritic, recrystallized structure. Grains have different sizes,

Credit HE-Arc CR.




Fig. 7: Micrograph of the metal sample (detail of Fig. 6), etched, bright field. Ferrite grains including Neumann bands formed after cold working in a P-rich iron,

Credit HE-Arc CR.

Microstructure	Recrystallized grains, Newman bands, ghost structure
First metal element	Fe
Other metal elements	P

Complementary information

None.


Corrosion layers

The remaining metal, including the large crack, is covered by a thin, fissured corrosion crust (Figs. 3, 4, 6 and 8). The corrosion crust is thicker on the side containing the long slag inclusions (Fig. 3). In bright field and in the BSE-mode of the SEM image only light and dark-grey areas can be distinguished (Figs. 4 and 9). Under polarised light the corrosion products appear yellow-orange near the metal surface and then become successively dark-red and black. The outer layer (CP1) is orange-yellow, as is the inner one (CP4, Fig. 8). There is a correlation between the level of grey in SEM/BSE-mode, the colours under polarised light, and the chemical composition of the corrosion layer (Table 3, Figs. 8 and 9). The lighter the grey of the SEM/BSE-mode, or the colours (light-brown and red) under polarised light, the

richer the area is in Fe and the more depleted it is in O. Surprisingly the inner corrosion layers (CP3 and CP4) are contaminated with Si, Al and O.


Elements	O	Si	Fe	Total
Light or dark-red corrosion products (CP3)	25	1.6	67	94
Light or dark-red corrosion products (CP3)	32	<	74	108
Dark or dark-red corrosion products (CP2)	41	<	67	109

Table 3: Chemical composition (mass %) of the corrosion layer (from Fig. 9). Method of analysis: SEM/EDS, Laboratory of Analytical Chemistry, Empa.



Credit HE-Arc CR.

Fig. 8: Micrograph showing the metal - corrosion crust interface from Fig. 3 (inverted picture, rotated by 135°, detail) and corresponding to the stratigraphy of Fig. 10, unetched, polarised light. The metal appears in blue and the corrosion changes from yellow-orange (CP4) to dark-red (CP3), black (CP2) and orange (CP1). The area selected for elemental chemical distribution (Fig. 9) is marked by a red rectangle,



Credit HE-Arc CR.

Fig. 9: SEM image, BSE-mode, and elemental chemical distribution of the selected area from Fig. 8. Method of examination: SEM/EDS, Laboratory of Analytical Chemistry, Empa.,

Corrosion form Uniform - transgranular

Corrosion type Unknown

Complementary information

None.

∨ MiCorr stratigraphy(ies) – CS




Fig. 10: Stratigraphic representation of the sample taken from the sword in cross-section (dark field) using the MiCorr application. The characteristics of the strata are only accessible by clicking on the drawing that redirects you to the search tool by stratigraphy representation. This representation can be compared to Fig. 8, Credit HE-Arc CR.

∨ Synthesis of the binocular / cross-section examination of the corrosion structure

None.

∨ Conclusion

The sword blade is made of a hard, P-rich iron. It displays poor workmanship compared to other Celtic swords. The metal was first hot worked followed by a final cold working. The corrosion layer, typical of terrestrial context, has been partially removed by the conservation treatment. The possible use of air abrasive cleaning with glass beads and aluminium oxide, or the use of abrading tools, could explain the enrichment in Si and Al of the surface.

∨ References

References on object and sample

References object

1. Senn Bischofberger, M. (2005) Das Schmiedehandwerk im nordalpinen Raum von der Eisenzeit bis ins frühe Mittelalter. Internationale Archäologie, Naturwissenschaft und Technologie Bd. 5, (Rahden/Westf.), 30.

References sample

2. Senn Bischofberger, M. (2005) Das Schmiedehandwerk im nordalpinen Raum von der Eisenzeit bis ins frühe Mittelalter. Internationale Archäologie, Naturwissenschaft und Technologie Bd. 5, (Rahden/Westf.), 240-242.

References on analytic methods and interpretation

3. Swiss, A. J. and McDonnell, J.G. (2003) Evidence and interpretation of cold working in ferritic iron. International Conference, Archaeometallurgy in Europe 2003, Proceedings, vol. 1, Milan, 209-217.

4. ASTM E112-13: Standard Test Methods for Determining Average Grain Size.